

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
18 December 2003 (18.12.2003)

PCT

(10) International Publication Number
WO 03/104532 A1(51) International Patent Classification⁷: C25D 15/00,
H01R 13/03, C25D 7/00

(21) International Application Number: PCT/EP03/06034

(22) International Filing Date: 5 June 2003 (05.06.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02077255.4 5 June 2002 (05.06.2002) EP

(71) Applicant (for all designated States except US): HILLE & MÜLLER GMBH [DE/DE]; Am Trippelsberg 48, 40589 Düsseldorf (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HOLTkamp, Johannes, Henricus, Maria [NL/DE]; Walderstrasse 276, 40724 Hilden (DE). GIESLER, Martin [DE/DE]; Walter-Kolb-Strasse 15, 40764 Langenfeld (DE). CELIS, Jean-Pierre, Paul, Julien, Clement, Frans [BE/BE]; Bloesemlaan 21, B-3360 Korbeek-Lo (BE).

(74) Agent: KRUIT, Jan; Corus Technology BV, P.O. Box 10000, NL-1970 CA IJmuiden (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COMPONENTS FOR ELECTRICAL CONNECTORS, AND METAL STRIP THEREFORE

(57) Abstract: Electrical connector or electrical switching element comprising a metallic core and a galvanically deposited metal containing coating layer, whereby the metal containing coating layer is deposited by electrolytic composite plating and the coating layer comprises a metal matrix and distributed therein particles selected from the group of particles having electrically conductive properties, particles having lubricating properties, particles having wear resistance properties and particles having properties of increasing the temperature durability or combinations of particles from those groups, wherein the electrical connector or electrical switching element has been made from a continuously coated metal strip comprising a metallic core and a galvanically deposited metal containing coating layer. Continuously coated metal strip for manufacturing such electrical connectors.

WO 03/104532 A1

COMPONENTS FOR ELECTRICAL CONNECTORS, AND METAL STRIP THEREFORE

The invention relates to components for electrical connectors or electrical
5 switching elements comprising a metallic core and a galvanically deposited metal
containing composite coating layer.

The invention also relates to a method for the manufacture of such components, to
metal strips for the manufacture of such components, to the use of such metal strip for
the manufacture of an electrical connector, and to a method for manufacturing such
10 metal strips.

In connection with the present application an electrical connector is to be
understood as any means for making an electrical connection between two parts, such
as but not limited to temporarily, permanently, by hand, by mechanical or electrical
force, in single or multiple form.

15 It is well known to use metal components for connectors, the components having
a metallic core and a galvanically deposited metal containing coating layer, the coating
layer being applied to get an improved electrical conductivity, an improved lubrication,
an improved wear resistance and/or an improved temperature durability. Such coating
layer can be applied over the total surface of the metal components, or only over part or
20 the surface, such as certain tracks on the surface. Coating examples are for instance
silver and gold, which achieve good results. Other coating layers, such as tin or nickel
layers, often result in a lesser or shorter-lived improvement.

To improve the properties of such cheaper layers it is known to incorporate
special particles in the coating layer. Such particles are selected from the group of
25 particles having electrically conductive properties, particles having lubricating
properties, particles having wear resistance properties, and particles having properties
of increasing temperature stability or combinations of particles from those groups.

Patent publication 5,028,492 relates to a composite coating for connectors. The
composite coating comprises a ductile metal matrix of a selected composition and a
30 uniformly dispersed polymer component. In one embodiment of a method of applying
the composite coating it is proposed to deposit the coating directly on a connector in an
electroless or electrolytic plating process.

However, due to the separate or batchwise application of the coating on the metal components, the coated components are expensive.

To reduce costs it is known to first coat a metal strip and after that manufacture the components for the electrical connectors or electrical switching elements from that strip.

A metal strip for use in electrical connectors is known from EP 0 849 373 A1. That publication discloses a metal strip from copper, iron, nickel, zinc or its alloys as metallic core which is coated with a coating layer mainly consisting of tin or tin alloy. In the most outer skin of the coating layer, 1 to 50 atomic weight percent of carbon is incorporated. The purpose of the incorporation of carbon is to obtain an improved wear- and corrosion behaviour, in particular fretting corrosion, while at the same time having an oxide free surface.

That method for making the metal strip comprises applying a tin coating layer by hot dip tinning or electrolytic tin-plating into the metallic core. Subsequently, the metallic core with the tin coating layer is fed through an oil bath at elevated temperature above the melting point of the tin or the tin alloy to incorporate carbon in the tin coating layer. Preferably, to obtain a higher carbon content, the metal strip is cooled in a second oil bath.

A problem with the known method is that at least one additional process step after applying the coating layer is required.

Another problem is that the method can only be applied to coating layer metals of relatively low melting points.

A further problem is that only carbon can be incorporated as the component to improve the desired characteristics of the metal strip as starting material for electrical connectors.

However, carbon only provides a solution for some, but not all requirements of electrical connections. So, the proposed method is only applicable for a limited number of applications of electrical connectors.

It is an object of the present invention to provide components for electrical connectors with a large amount of particles in the coating layer, preferably all throughout the coating layer.

It is a further object of the present invention to provide components for electrical connectors in which the coating layer has properties that are optimally adapted to the intended use of the electrical connectors.

It is yet a further object of the present invention to provide such components for
5 electrical connectors that are inexpensive.

It is another object of the present invention to provide a metal strip for the manufacture of components for electrical connectors that can be manufactured in a single process step.

It is a further object of the present invention to provide a metal strip for the
10 manufacture of components for electrical connectors which gives more freedom in the selection of the metal matrix of the coating layer and of the particles embedded therein.

According to a first aspect of the invention, these and other advantages are obtained with an electrical connector or electrical switching element comprising a metallic core and a galvanically deposited metal containing coating layer, the metal
15 containing coating layer being deposited by electrolytic composite plating and the coating layer comprises a metal matrix and distributed therein particles selected from the group of particles having electrically conductive properties, particles having lubricating properties, particles having wear resistance properties and particles having properties of increasing the temperature durability or combinations of particles from
20 those groups, wherein the electrical connector or electrical switching element has been made from a continuously coated metal strip comprising the metallic core and the galvanically deposited metal containing coating layer. This process is also referred to as co-deposition in this application.

According to the present invention the metal containing coating layer is deposited
25 on an essentially flat metal strip. This brings the advantage of good controllability of the co-deposition process, a good uniformity of the thickness of the coating layer and a good homogeneity of the distribution of the particles within the coating layer, because side-effects are eliminated and non-uniform distribution of the electrical field is prevented.

30 There are, depending on the application, several requirements an electrical connector should fulfil. A first requirement is a low electrical resistance. The electrical

resistance may increase over time due to corrosion of the outermost layer of the material of which the contacts of the connector are manufactured.

Also effects, known as tribo-oxidation or fretting may occur. In case the electrical connectors are used in a vibrating environment, closed contacts may move slightly in a tangential direction, relative to each other, thereby disrupting a formed oxide layer that can act as an abrasive, exposing non-oxidised contact material to the atmosphere. The abraded particles may deposit between the closed contacts, thereby increasing the contact resistance.

A relative movement of the closed contacts may also be caused through thermal expansion of the used materials. Through changes of the environmental temperatures or as a consequence of heat generation caused by the current passing through closed contacts, the connector may change in temperature causing relative movement of the closed contacts. This may also lead to tribo-oxidation.

Another important characteristic of a connector is the insertion force needed to insert a first part of a connector into the co-operating second part of the connector. Related hereto is the extraction force needed to disengage a connector.

The metal strip according to the invention can be given the selected, optimum characteristics in dependence of the selection of the particles embedded in the coating layer. The most important characteristics being low contact resistance, low oxidation, high corrosion resistance, low tribo-oxidation or fretting, low insertion and extraction forces.

By selecting particles having high electrical conductivity a low contact resistance can be obtained. The low contact resistance is maintained even when the metal of the metal matrix oxidises at its surface, in particular in the event the particles protrude from the metal matrix.

By selecting particles having lubricating properties, a low insertion and/or extraction force can be obtained when the particles protrude from the metal matrix. An additional advantage is that fretting is also reduced.

By selecting particles having high wear resistance properties it is achieved that under vibrating conditions or in applications requiring frequent insertions and extractions, contact wear is reduced. Consequently, fewer particles are rubbed off and

built up between the contacts. This has the effect that the contact resistance increases less over time and/or use.

By selecting particles having heat resistance and conductive properties it is achieved that under high temperature conditions, the contact resistance remains low and/or corrosion or oxidation is low, i.e. the characteristics of the electrical connector are less temperature and time dependent. The particles having conductive properties will make sure that the conductivity stays low, even if part or all of the coating layer oxidises.

Preferred embodiments of the invention are given in the dependent claims.

10 In claim 2, soot and graphite have a good electrical conductivity; they are moreover cheap and insoluble in most aqueous solutions. Carbon nanotubes have an excellent electrical conductivity, and are insoluble in most aqueous solutions. The ceramic particles TiN, TiB, CrN, TiS, TaS₂, MoS₂ and TiO are well known conductive materials, readily available, and insoluble in most aqueous solutions.

15 PTFE, polyimide and polyamide as mentioned in claim 3 are well known for their lubricating properties, they are readily available, and insoluble in most aqueous solutions.

In claim 4, the ceramic particles as mentioned in claim 2 have a high wear resistance. Also carbon nanotubes have a high wear resistance.

20 Pure carbon, graphite, MoS₂, BN and other particles as mentioned in claim 5 are well known for their lubricating properties.

The metals mentioned in claim 6 are established materials in electroplating, and inexpensive. The selection of the metal of the metal matrix can be based on the purpose for which the electrical connector is used and the conditions of use.

25 The metal used for the metal core can be selected from a wide range of metals, also dependent on the purpose for which the electrical connector is used and the conditions of use. The metals mentioned in claim 7 are commonly used metals for use in connectors.

30 By co-depositing the metal of the metal matrix and the particles, it is possible to select the size of the particles within a broad range, such as between 0.001 μm and 15 μm , dependent on the composition of the particles and their purpose in the coating layer. Size is to be interpreted as the diameter of the smallest sphere enclosing a

particle. The maximum size is determined by the thickness of the coating; larger particles are difficult to incorporate and give a non-homogeneous distribution of the properties to be achieved. Particles smaller than 1 nm lose their properties as particle.

Preferably the particles have a size in the range of 0.1 μm and 15 μm , because
5 particle smaller than 0.1 μm are difficult to incorporate in metal layers and difficult to disperse in aqueous solutions without coagulating.

This co-depositing also makes it possible to embed a broad range of volume fractions of the distributed particles in the coating layer, again dependent on the requirements during operation or the lifetime of the electrical connector. Preferred is a
10 volume fraction of the distributed particles in the co-deposited coating layer in the range of 0.7% to 30% of the volume of the coating layer. The volume fraction also depends on the type of particle used. Below 0.7% the particle will not be effective. Above 30% the co-deposited coating will lose its coherence.

A thickness of the strip between 0.1 and 1.5 mm is best suited for manufacturing
15 electrical connector and switching elements.

Since the process of co-depositing on a flat strip is very well controllable, the thickness of the coating layer can be matched very well to the requirements put on the connectors. Coating layers in the range of 0.2 – 10 μm are preferred. Thinner layers in general do not meet the requirements; for thicker layers alternative processes could be
20 considered in view of the time required for the co-deposition of the metal matrix and the distributed particles makes it possible to homogeneously distribute the particles in thickness direction within the coating layer. The coating layer, therefore, also has uniform characteristics over the thickness and the total coating layer does not need to be thicker than required for normal operation during the lifetime of the connector or the
25 apparatus in which the connector is used.

According to a second aspect, the invention is also embodied in a method for the manufacture of components for electrical connectors according to the first aspect of the invention, wherein a metallic core is fed through a galvanic bath and a coating layer is deposited in a continuous or semi-continuous manner on at least one side of the metallic
30 core.

Due to the continuous or semi-continuous co-deposition of the matrix of metal and particles, an inexpensive strip is provided from which the electrical components can be manufactured.

According to a third aspect of the invention, there are provided continuously
5 coated metal strips for the manufacture of components for electrical connectors or electrical switching elements, such as described in the first aspect of the invention. The metal strips as described in claims 14 to 18 are suitable for fabricating these components. The advantages of such strips will be clear from the discussion of the first and second aspect of the invention. The most important aspect is that such continuously
10 coated strips with the co-deposited layer of a metal matrix with incorporated particles is less expensive to produce than the known strips.

The invention also relates to the use of such a continuously coated strip, and to a method to manufacture such a continuously coated metal strip.

The method makes it possible to apply in one single process step a metal matrix
15 and distribution therein particles which can be selected from a wide range of materials, dependent on the desired characteristics of the composite coating layer.

The invention will be elucidated referring to the following experiments and results.

In the following 7 examples, a metal strip has been coated by co-deposition with a
20 matrix of a metal containing particles. The particles provide an extra electrical conductivity, lubrication, wear resistance and/or temperature durability.

Example 1: nickel graphite coating with graphite particles on steel

Steel strip is plated with a co-deposit nickel-graphite coating in a continuous plating
25 line. The line is a vertical plating line with a total anode area of 300 dm². The steel strip has a thickness of 0.2 – 0.4 mm and it will be first degreased, rinsed, activated in sulfuric acid, and again rinsed. Next the steel strip is plated with nickel-graphite co-deposit coating:

Bath composition:

Nickel	79 g/l
Chloride	27 g/l
Boric Acid	35 g/l
Graphite	48 g/l
Surfactant	0.5 g/l
PH	2.8
Temperature	60 °C
Current density	15 A/dm ²
Strip velocity	11 m/min
Coating thickness	1 µm

All the above values are approximate values. The coating contains approximately 9 % graphite. The graphite particles are non-spherical and on average have a size of approximately 5 µm.

Example 2: nickel coating with graphite particles on copper

Similar to example 1, but now the steel strip is substituted by a copper strip. Here the coating is the same as in example 1 and again the coating contains approximately 9 % graphite particles.

Example 3: nickel coating with TiN particles on steel

Similar to example 1, but now the graphite particles are substituted by titanium nitride particles (40 g/l). The TiN particles are spherical and have a diameter of approximately 5 µm. The coating contains approximately 3 % TiN particles.

Example 4: nickel coating with TiN and graphite on steel

Similar to example 3, extra amount of 40 g/l graphite was added. The coating contains approximately 3 % graphite particles and 3 % TiN particles.

Example 5 tin coating with graphite on steel

Similar to example 1, but the nickel is substituted by tin.

Bath composition:

NaOH	10 g/l
NaSnO ₃	100 g/l
graphite	20 g/l
PH	13
Temperature	75 °C
Current density	2.5 A/dm ²
Strip velocity	4 m/min
Coating thickness	1 µm

Here the current density has to be low in view of the deposition of tin. The coating contains approximately 1 % graphite particles.

5

Example 6: nickel coating with CrN particles on steel

Similar to example 3, but the TiN particles are substituted by CrN particles. The CrN particles are spherical and have a diameter of approximately 5 µm. The coating contains approximately 3 % CrN particles.

10

Example 7: copper coating with PTFE particles on steel

The same co-deposition line has been used as in example 1, but nickel has been substituted by copper and graphite by PTFE.

15

Bath composition:

Coppersulfate	200 g/l
Sulfuric acid	70 g/l
PTFE	30 g/l
Surfactants	160 mg/l
PH	0.4
Temperature	50 °C
Current density	5 A/dm ²
Strip velocity	2 m/min
Coating thickness	2 µm

The PTFE particles are spherical and have a diameter of approximately 0.3 µm. The coating contains approximately 25 volume% (or 8 weight%) PTFE particles.

20

All percentages above are in weight%, unless otherwise specified.

The coated metal has been tested, and to be able to compare it with coating layers without particles, some control test have been performed on a metal substrate (steel) having a coating layer of pure nickel or pure tin.

The tests have been performed to measure the contact resistance, see table 1, the friction coefficient, see table 2, the wear resistance, see table 3, and the temperature durability, see table 4.

For the contact resistance measurement the sample was placed at 8 bar pressure, and measured under DC conditions in a 4-point manner. Coefficient of friction was measured together with the wear resistance measurement in a fretting test.

Table 1: contact resistance of various composite plated systems in mOhm.cm²

Material	Resistance in mOhm.cm ²
Control (nickel)	90
Nickel-graphite	19
Nickel-titaniumnitride	18
Nickel-chromiumnitride	18

Table 2: friction coefficient of various composite plated systems

Control (nickel)	0.6
Nickel-graphite	0.15
Nickel-PTFE	0.07
Control (copper)	0.9
Copper-PTFE	0.08
Control (tin)	0.7
Tin-graphite	0.4

Table 3: wear resistance. Size of the wear track after fretting test in micrometers

Control (nickel)	700
Nickel-PTFE	200
Nickel-graphite	400
Copper-PTFE	200

Table 4: temperature durability: contact resistance after exposure for prolonged time at 250 C

Control 1 (nickel)	600
Control 2 (tin)	total degradation
Nickel-graphite	34

The tables clearly show that in all cases the co-deposition of the selected particles in the
5 nickel or tin coating provides a major improvement over the pure nickel or tin layer.

CLAIMS

1. Electrical connector or electrical switching element comprising a metallic core and a galvanically deposited metal containing coating layer, the metal containing
5 coating layer being deposited by electrolytic composite plating and the coating layer comprises a metal matrix and distributed therein particles selected from the group of particles having electrically conductive properties, particles having lubricating properties, particles having wear resistance properties and particles having properties of increasing the temperature durability or combinations of
10 particles from those groups, characterised in that the electrical connector or electrical switching element has been made from a continuously coated metal strip comprising the metallic core and the galvanically deposited metal containing coating layer.
- 15 2. Electrical connector or electrical switching element according to claim 1, characterized in that the electrically conductive particles are selected from the group comprising carbonaceous materials such as soot, graphite and carbonaceous nanotubes, and electrically conductive ceramic materials comprising borides, such as titanium boride and iron boride; nitrides such as titanium nitride and chromium
20 nitride; sulfides such as titanium sulfide, tantalum disulfide and molybdeen disulfide, and electrically conductive oxides such as titanium oxide.
3. Electrical connector or electrical switching element according to claim 1 or 2, characterized in that the particles having lubricating properties are selected from
25 the group comprising polymers, such as PTFE, polyimide and polyamide, carbon containing particles such as essentially pure carbon and graphite, ceramic particles such as molybdeen disulphide and borium nitride, and lubricating means containing capsules such as capsules containing polyphenylether or organic lubricating means, and optionally the particles having lubricating properties also
30 having corrosion inhibiting additives.

4. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the particles having wear resistance properties are selected from the group comprising ceramic particles such as aluminium oxide, zirconium oxide, silicon carbide, boron nitride and titanium nitride, and optionally carbonaceous nanotubes.
5
5. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the particles having properties of increasing temperature durability are selected from the group comprising heat resistant and conductive ceramic particles such as aluminium oxide, zirconium oxide, silicon carbide, diamond-like boron nitride and titanium nitride, and carbonaceous materials such as soot, graphite and carbonaceous nanotubes.
10
6. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the co-deposited metallic matrix of the coating layer on the continuously coated metal strip mainly comprises one or more metals selected from the group nickel, copper, tin, zinc, chromium and alloys or combinations thereof.
15
7. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the metallic core mainly comprises one or more metals selected from the group low carbon steel, high-strength steel, stainless steel, copper, including bronze and brass and multilayer composites alloys or mixtures thereof.
20
8. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the distributed particles have a size in the range of 0.001 – 15 μm , preferably in the range of 0.1 – 15 μm .
25
9. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the volume fraction of the distributed
30

particles in the co-deposited coating layer is in the range of 0.7% to 30% of the volume of the coating layer.

- 5 10. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the thickness of the metal strip is in the range of 0.1 to 1.5 mm.
- 10 11. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the coating layer has a thickness in the range from 0.2 – 10 μm , preferably in the range of 1 – 5 μm .
- 15 12. Electrical connector or electrical switching element according to any one of the preceding claims, characterized in that the particles of at least one group, preferably of all groups of particles, are homogeneously distributed in the coating layer.
- 20 13. Method for the manufacture of an electrical connector or electrical switching element according to any of the claims 1 to 12, characterized in that a metallic core is fed through a galvanic bath and a coating layer is deposited on at least one side of the metallic core in a continuous or semi-continuous manner, wherein a metal matrix and particles selected from the group of particles having electrically conductive properties, particles having lubricating properties, particles having wear resistance properties or particles having properties of increasing temperature stability and combinations thereof, are co-deposited on the metal core to form the
25 coating layer, and the electrical connector or electrical switching element is manufactured from the coated metal core.
- 30 14. Continuously coated metal strip for the manufacture of components for electrical connectors or electrical switching elements comprising a metallic core and a galvanically deposited metal containing coating layer, the metal containing coating layer being deposited by electrolytic composite plating and the coating

layer comprises a metal matrix and distributed therein particles selected from the group of particles having wear resistance properties.

15. Continuously coated metal strip according to claim 14, wherein the particles
5 having wear resistance properties are selected from the group comprising ceramic particles such as aluminium oxide, zirconium oxide, silicon carbide, boron nitride and titanium nitride, and optionally carbonaceous nanotubes.
16. Continuously coated metal strip for the manufacture of components for electrical
10 connectors or electrical switching elements comprising a metallic core and a galvanically deposited metal containing coating layer, the metal containing coating layer being deposited by electrolytic composite plating and the coating layer comprises a metal matrix and distributed therein particles selected from the
15 group of electrically conductive particles, selected from the group comprising electrically conductive ceramic materials comprising borides, such as titanium boride and iron boride; nitrides such as titanium nitride and chromium nitride; sulfides such as titanium sulfide, tantalum disulfide and molybdeen disulfide, and electrically conductive oxides such as titanium oxide.
- 20 17. Continuously coated metal strip for the manufacture of components for electrical connectors or electrical switching elements comprising a metallic core and a galvanically deposited metal containing coating layer, the metal containing coating layer being deposited by electrolytic composite plating and the coating
25 layer comprises a metal matrix and distributed therein particles selected from the group of particles having lubricating properties, selected from the group comprising polymers, such as PTFE, polyimide and polyamide, ceramic particles such as molybdeen disulphide and borium nitride, and lubricating means containing capsules such as capsules containing polyphenylether or organic
30 lubricating means.
18. Continuously coated metal strip for the manufacture of components for electrical connectors or electrical switching elements comprising a metallic core and a

galvanically deposited metal containing coating layer, the metal containing coating layer being deposited by electrolytic composite plating and the coating layer comprises a metal matrix and distributed therein particles selected from the group of particles having properties of increasing temperature durability, selected from the group comprising heat resistant and conductive ceramic particles such as aluminium oxide, zirconium oxide, silicon carbide, diamond-like boron nitride and titanium nitride.

19. Use of a continuously coated metal strip according to any one of the claims 14-18 in the manufacture of an electrical connector or electrical switching element.

20. Method for the manufacture of a continuously coated metal strip according to any of the claims 14 to 18, characterized in that a metallic core is fed through a galvanic bath and a coating layer is deposited on at least one side of the metallic core in a continuous or semi-continuous manner, wherein a metal matrix and particles selected from the group of particles having electrically conductive properties, particles having lubricating properties, particles having wear resistance properties or particles having properties of increasing temperature stability and combinations thereof, are co-deposited on the metal core to form the coating layer.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 03/06034

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C25D15/00 H01R13/03 C25D7/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C25D H01R

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 199921 Derwent Publications Ltd., London, GB; Class L03, AN 1998-205933 XP002219395 & SE 510 043 C (ABB RES LTD), 12 April 1999 (1999-04-12)	1-5, 8, 14-19
A	abstract	9, 13, 20
X	WO 98 23444 A (LEARONAL INC) 4 June 1998 (1998-06-04) page 12, line 3-7 page 13, line 1 -page 14, line 7	1-3, 6-8, 16, 17, 19
A	page 24, paragraph 1	11, 13, 20
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

6 November 2003

Date of mailing of the international search report

14/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Zech, N

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/06034

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US 4 652 349 A (BEHRINGER GEORG ET AL) 24 March 1987 (1987-03-24) column 1, line 7-13 examples	1-3,6, 16-19 11
X A	US 6 360 437 B1 (ITOH SHIGENORI ET AL) 26 March 2002 (2002-03-26) claims 1,7-10,12 column 6, line 4-12	1,2,4-8, 11,12, 14-16, 18,19 13,20
X A	US 5 853 557 A (MOLVAR ALLEN E ET AL) 29 December 1998 (1998-12-29) abstract column 11, line 1-28 claims 1,9-11,13,14	1,3,6-9, 11,13, 17,19,20
X A	US 5 967 860 A (RICKETTS MARK ET AL) 19 October 1999 (1999-10-19) column 3, line 53-65 column 6, line 19-22,32,33 column 2, line 36-51	1,3,6,7, 9,11,12, 17,19 13,20
X A	US 5 028 492 A (GUENIN BRUCE M) 2 July 1991 (1991-07-02) cited in the application column 3, line 53-62 column 5, line 1-22,41-60 column 5, line 67 -column 6, line 19	1,3,6,8, 9,11,12, 17,19
X A	US 3 672 970 A (TOMASZEWSKI THADDEUS W) 27 June 1972 (1972-06-27) column 1, line 10-41 column 2, line 44-67 column 4, line 45-58,64-71 column 5, line 22-33	14,15, 17,18 1,3-6,8, 9,12,13, 20
X A	US 3 756 925 A (OKAMOTO Y ET AL) 4 September 1973 (1973-09-04) column 3, line 43-72 column 4, line 14-16,62 examples claims 1,7	17 1,3, 6-10,13, 20

-/-

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/06034

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	EP 0 630 993 A (SUMITOMO METAL IND) 28 December 1994 (1994-12-28) page 3, line 57 -page 4, line 24 page 6, column 3-6 page 10, line 36 claim 7	17 1,3,6, 9-11,13, 20
A	DE 197 02 366 A (TOYODA GOSEI KK) 7 August 1997 (1997-08-07) abstract column 1, paragraph 2 column 5, line 42-58	1-6, 13-18,20
A	US 6 319 308 B1 (MCCOMAS EDWARD) 20 November 2001 (2001-11-20) column 1, paragraph 1 column 2, paragraphs 4,6 column 3, line 19-23 column 4, line 10-14 example 1	1,3-8, 13-15, 17,18,20
A	DE 43 41 537 A (FORD WERKE AG) 9 June 1994 (1994-06-09) abstract figure 111	1,13,14, 16-18,20
A	EP 0 285 931 A (NIPPON STEEL CORP) 12 October 1988 (1988-10-12) figure 8 claims 1,2 page P, paragraph 1	1,13,14, 16-18,20

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/06034

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
SE 510043	C	12-04-1999	SE 510043 C2 SE 9602233 A	12-04-1999 07-12-1997
WO 9823444	A	04-06-1998	WO 9823444 A1	04-06-1998
US 4652349	A	24-03-1987	DE 3665886 D1 EP 0195995 A1 JP 61227196 A	02-11-1989 01-10-1986 09-10-1986
US 6360437	B1	26-03-2002	NONE	
US 5853557	A	29-12-1998	US 5667659 A EP 0914691 A1 JP 2000508379 T KR 2000005262 A WO 9738469 A1	16-09-1997 12-05-1999 04-07-2000 25-01-2000 16-10-1997
US 5967860	A	19-10-1999	NONE	
US 5028492	A	02-07-1991	AU 7571491 A WO 9113754 A1 US 5141702 A	10-10-1991 19-09-1991 25-08-1992
US 3672970	A	27-06-1972	NONE	
US 3756925	A	04-09-1973	JP 49020459 B	24-05-1974
EP 0630993	A	28-12-1994	DE 69400509 D1 DE 69400509 T2 EP 0630993 A1 EP 0633329 A1 JP 7070795 A JP 3358297 B2 JP 7070796 A KR 166607 B1 KR 167050 B1 US 5618634 A JP 7070794 A	17-10-1996 10-04-1997 28-12-1994 11-01-1995 14-03-1995 16-12-2002 14-03-1995 15-01-1999 01-05-1999 08-04-1997 14-03-1995
DE 19702366	A	07-08-1997	JP 3282478 B2 JP 9202996 A JP 9263989 A JP 10008289 A JP 10195690 A DE 19702366 A1 US 5865976 A	13-05-2002 05-08-1997 07-10-1997 13-01-1998 28-07-1998 07-08-1997 02-02-1999
US 6319308	B1	20-11-2001	CA 2432100 A1 EP 1352108 A1 WO 02052063 A1	04-07-2002 15-10-2003 04-07-2002
DE 4341537	A	09-06-1994	CA 2102999 A1 DE 4341537 A1 GB 2273109 A ,B JP 6235057 A US 5514422 A	08-06-1994 09-06-1994 08-06-1994 23-08-1994 07-05-1996
EP 0285931	A	12-10-1988	JP 1177386 A	13-07-1989

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/06034

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0285931	A	JP 2036443 C	28-03-1996
		JP 7065218 B	12-07-1995
		JP 1191797 A	01-08-1989
		JP 6099836 B	07-12-1994
		JP 1191798 A	01-08-1989
		JP 1215997 A	29-08-1989
		JP 2628331 B2	09-07-1997
		JP 1215998 A	29-08-1989
		JP 2631683 B2	16-07-1997
		JP 1630597 C	26-12-1991
		JP 2051996 B	09-11-1990
		JP 63243295 A	11-10-1988
		JP 1039398 A	09-02-1989
		JP 2707085 B2	28-01-1998
		JP 1039399 A	09-02-1989
		JP 2562607 B2	11-12-1996
		JP 1055397 A	02-03-1989
		JP 2107472 C	06-11-1996
		JP 8009796 B	31-01-1996
		JP 1055398 A	02-03-1989
		JP 6035673 B	11-05-1994
		JP 1079393 A	24-03-1989
		JP 1079382 A	24-03-1989
		JP 7088584 B	27-09-1995
		JP 1162794 A	27-06-1989
		JP 1162795 A	27-06-1989
		JP 7015153 B	22-02-1995
		AU 597163 B2	24-05-1990
		AU 1389788 A	20-10-1988
		CA 1336698 C	15-08-1995
		CA 1336699 C	15-08-1995
		CA 1336700 C	15-08-1995
		CA 1337054 C	19-09-1995
		DE 3882769 D1	09-09-1993
		DE 3882769 T2	11-11-1993
		EP 0285931 A1	12-10-1988
		KR 9102186 B1	06-04-1991
		US 4897317 A	30-01-1990
		US 4877494 A	31-10-1989